



PRODUCT INFORMATION LETTER

PIL CRP/14/8399
Dated 20 Mar 2014

Lead frame 2nde source qualification

Sales Type/product family label	NA
Type of change	Package assembly material change
Reason for change	DCI supplier announced recently his "stamped" lead frame activity
Description	This change is concerning the qualification of a 2nd source for "stamped" lead frames currently provided by our supplier DCI.
Forecasted date of implementation	29-Mar-2014
Forecasted date of samples for customer	29-Mar-2014
Forecasted date for STMicroelectronics change Qualification Plan results availability	29-Mar-2014
Involved ST facilities	Muar, Bouskoura and Carsem

DOCUMENT APPROVAL

Name	Function
Livache, Veronique	Corporate Quality Manager
Low, Patrick	Process Owner

Lead frame 2nd source qualification

WHAT is the change?

This change is concerning the qualification of a 2nd source for “stamped” lead frames currently provided by our supplier DCI.

Packages and manufacturing plants concerned by this change are listed in the table below:

Plant	Package
Muar	PSSO24
Muar	SO20L
Muar	SO28
Muar	SO34
Bouskoura	PwSSO12
Bouskoura	PwSSO14
Carsem (Subcontractor)	SOT23, SOT323, SO24, TSSOP

WHY:

Reason for this change is:

- Our lead frame supplier DCI announced recently his “stamped” lead frame activity closure.
- A second source qualification has been immediately activated to protect our customers and business.

WHEN will this change occur?

Plant	Package	Production start date
Muar	PSSO24	W13 2014
Muar	SO20L	W36 2014
Muar	SO28	W13 2014
Muar	SO34	W16 2014
Bouskoura	PwSSO12	W31 2014
Bouskoura	PwSSO14	W31 2014
Carsem (Subcontractor)	SOT23, SOT323, SO24, TSSOP	W36 2014

HOW will the change be qualified?

- Second source suppliers are already identified:

Plant	Package	Identified second source
Muar	PSSO24	SHINCO
Muar	SO20L	SHINCO
Muar	SO28	SUMITOMO
Muar	SO34	SUMITOMO
Bouskoura	PwSSO12	SUMITOMO
Bouskoura	PwSSO14	SUMITOMO
Carsem (Subcontractor)	SOT23, SOT323, SO24, TSSOP	MITSUI, POSSEHL (*)

(*): MITSUI & POSSEHL will use the tools transferred by DCI.

- Approach for selecting the second source supplier is: same specifications, same materials, same finishing
- Risk have been evaluated (APPENDIX 1)
- This change will be qualified using the standard STMicroelectronics procedures for quality and reliability. Major steps of the qualification are:
 - Process capability assessment
 - Workability
 - Reliability
 - Line stressing

IMPACTS OF THE CHANGE:

Form: No change
Fit: No change
Function: No change

APPENDICES:

APPENDIX 1 Risk assessment
APPENDIX 2 Qualification plan
APPENDIX 3 Qualification results

APPENDIX 1: RISK ASSESSMENT

#	Risks identified	Potential risk resulting from	Class	Considered action
1	Workability issues on machines at different process step (Die attach, wire bonding, molding, plating, cropping)	Indexing holes with different positions Frame dimension(X, Y, thickness) different from actual ones	Low	Drawings check Samples verifications validation during workability exercise
2	Transport problems in magazines (D/Attach, wire bonding, molding)	Frame dimension(X, Y, thickness) different from actual sizes	Low	Drawings check Samples verifications validation during workability exercise
3	D/A Quality problem	Results not in accordance with ST requirements on following: - void - coverage - Bond line thickness - Die shear	Medium	Reinforced checks to be done during execution of Quality plan and line stressing
4	Wire bonding quality problems	Results not in accordance with ST requirements on following: - Non-stick on Leads (NSOL) . Poor bondability of 2 nd bond - Pull test	Medium	Reinforced checks to be done during execution of Quality plan and line stressing
5	Molding quality problems	Results not in accordance with ST requirements on following: - Excessive resin flash - molding voids	Medium	Reinforced checks to be done during execution of Quality plan and line stressing
6	Deflash / Plating quality issues	Results not in accordance with ST requirements on following: - plating thickness - plating quality	Medium	Reinforced checks to be done during execution of Quality plan and line stressing
7	Cropping quality problems	Results not in accordance with ST requirements on following: - crack package - package mismatch (dimension) - Metal burrs	Medium	Reinforced checks to be done during execution of Quality plan and line stressing
8	Product Performance	Electrical performances or characteristics change due to frame new material (resistivity...)	Low	Datalog on critical parameters (test) during qualification
9	Reliability Risks	- Delamination Frame/ Die - Delamination frame / Molding compound - Plating quality - contamination	Medium	Checks to be done during qualification, reliability, line stressing
10	Manufacturing issues	Yield degradation	Low	Yield variation between the existing material and new one to monitor during ramp up phase and line stressing after change

		Productivity issue	Low	Production and down time parameters to monitor carefully during ramp up phase and line stressing after deployment
11	Supply Chain: To guarantee parts delivery to our customers and avoid business disruption	No sufficient Buffer stock	Medium	Buffer stock of existing material to be secured by DCI to cover ST needs including the qualification period
		Unscheduled problems during deployment reducing the production throughput or degrading the yield or stopping the assembly activity	Medium	<ul style="list-style-type: none"> - Deployment plan to be carefully prepared - All opened points highlighted during qualification must be solved before moving to production
12	Supply Chain: Quality issues (ECC)	Quality or reliability problems in the field	Low	<ul style="list-style-type: none"> - Quality and reliability plans to be carefully verified to address potential product vulnerabilities - Extension of qual and reliability exercise until failure to know the margins available if needed

APPENDIX 2: Qualification plan

1) Reliability plan

Test Name	Conditions	Lots #	Sample Size	Notes
JLn	24 h bake @ 125C + MSLn TH soak + reflow simulation (3 times JEDEC J-STD -020C)	1 per L/F Option	160 pcs /lot	1, 2
JLn + TCT	Ta = -50/150C, 500 cycles	1 per L/F Option	77 pcs / lot	1,2,3
JLn + ES	ES = 100 TC (-50/150C) + 96 h PP (2 atm, 121C)	1 per L/F Option	45 pcs / lot	1, 4

Note	Description	Sample size
1	Electrical test	100%
2	SAM analysis in C and T mode to check delamination resin-die, resin-lead, resin-die pad , DA integrity	20pcs /lot min
3	Automotive products only: Wire pull test after de-capsulation (to collect pull strength and failure mode and to inspect by SEM all abnormal failure mode)	30 wire from 5 units min
4	VI inspection after de-capsulation to detect pad / metal corrosion	3 units/lot as min

2) Construction analysis

item	Sample size
<i>Visual inspection</i>	50
<i>POA</i>	10 x 3 lots
<i>Tin thickness</i>	30
<i>Tin composition</i>	30
<i>Wetting balance</i>	10
<i>Cross section</i>	1
<i>Silver spot thickness</i>	1
<i>Decapsulation</i>	5
<i>SAM</i>	10
<i>X RAY</i>	20
<i>Pull test</i>	30 bonds / 3 lots

APPENDIX 3: Qualification execution & results

Plant	Packages	Workability	Construction analysis	Reliability	Line stressing	Qualification completion
Muar	PSSO24	Passed	Passed	Passed	Passed	W13'2014
Muar	SO20	W16'2014	W23'2014	W27'2014	W27'2014	W36'2014
Muar	SO28	Passed	Passed	Passed	W12'2014	W13'2014
Muar	SO34	Passed	Passed	Passed	W15'2014	W16'2014
Bouskoura	PwSSO12	W13'2014	W19'2014	W21'2014	W29'2014	W31'2014
Bouskoura	PwSSO14	W13'2014	W19'2014	W21'2014	W29'2014	W31'2014
Carsem	SOT23 SOT323 SO24 TSSOP	W20'2014	NA	W30'2014	W35'2014	W36'2014

Please Read Carefully:

Information in this document is provided solely in connection with ST products. STMicroelectronics NV and its subsidiaries ("ST") reserve the right to make changes, corrections, modifications or improvements, to this document, and the products and services described herein at any time, without notice.

All ST products are sold pursuant to ST's terms and conditions of sale.

Purchasers are solely responsible for the choice, selection and use of the ST products and services described herein, and ST assumes no liability whatsoever relating to the choice, selection or use of the ST products and services described herein.

No license, express or implied, by estoppel or otherwise, to any intellectual property rights is granted under this document. If any part of this document refers to any third party products or services it shall not be deemed a license grant by ST for the use of such third party products or services, or any intellectual property contained therein or considered as a warranty covering the use in any manner whatsoever of such third party products or services or any intellectual property contained therein.

UNLESS OTHERWISE SET FORTH IN ST'S TERMS AND CONDITIONS OF SALE ST DISCLAIMS ANY EXPRESS OR IMPLIED WARRANTY WITH RESPECT TO THE USE AND/OR SALE OF ST PRODUCTS INCLUDING WITHOUT LIMITATION IMPLIED WARRANTIES OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE (AND THEIR EQUIVALENTS UNDER THE LAWS OF ANY JURISDICTION), OR INFRINGEMENT OF ANY PATENT, COPYRIGHT OR OTHER INTELLECTUAL PROPERTY RIGHT.

ST PRODUCTS ARE NOT DESIGNED OR AUTHORIZED FOR USE IN: (A) SAFETY CRITICAL APPLICATIONS SUCH AS LIFE SUPPORTING, ACTIVE IMPLANTED DEVICES OR SYSTEMS WITH PRODUCT FUNCTIONAL SAFETY REQUIREMENTS; (B) AERONAUTIC APPLICATIONS; (C) AUTOMOTIVE APPLICATIONS OR ENVIRONMENTS, AND/OR (D) AEROSPACE APPLICATIONS OR ENVIRONMENTS. WHERE ST PRODUCTS ARE NOT DESIGNED FOR SUCH USE, THE PURCHASER SHALL USE PRODUCTS AT PURCHASER'S SOLE RISK, EVEN IF ST HAS BEEN INFORMED IN WRITING OF SUCH USAGE, UNLESS A PRODUCT IS EXPRESSLY DESIGNATED BY ST AS BEING INTENDED FOR "AUTOMOTIVE, AUTOMOTIVE SAFETY OR MEDICAL" INDUSTRY DOMAINS ACCORDING TO ST PRODUCT DESIGN SPECIFICATIONS. PRODUCTS FORMALLY ESCC, QML OR JAN QUALIFIED ARE DEEMED SUITABLE FOR USE IN AEROSPACE BY THE CORRESPONDING GOVERNMENTAL AGENCY.

RESTRICTIONS OF USE AND CONFIDENTIALITY OBLIGATIONS:

THIS DOCUMENT AND ITS ANNEXES CONTAIN ST PROPRIETARY AND CONFIDENTIAL INFORMATION. THE DISCLOSURE, DISTRIBUTION, PUBLICATION OF WHATSOEVER NATURE OR USE FOR ANY OTHER PURPOSE THAN PROVIDED IN THIS DOCUMENT OF ANY INFORMATION CONTAINED IN THIS DOCUMENT AND ITS ANNEXES IS SUBMITTED TO ST PRIOR EXPRESS AUTHORIZATION. ANY UNAUTHORIZED REVIEW, USE, DISCLOSURE OR DISTRIBUTION OF SUCH INFORMATION IS EXPRESSLY PROHIBITED.

Resale of ST products with provisions different from the statements and/or technical features set forth in this document shall immediately void any warranty granted by ST for the ST product or service described herein and shall not create or extend in any manner whatsoever, any liability of ST.

ST and the ST logo are trademarks or registered trademarks of ST in various countries.

Information in this document supersedes and replaces all information previously supplied.

The ST logo is a registered trademark of STMicroelectronics. All other names are the property of their respective owners

© 2014 STMicroelectronics - All rights reserved.

STMicroelectronics group of companies

Australia - Belgium - Brazil - Canada - China - Czech Republic - Finland - France - Germany - Hong Kong - India - Israel - Italy - Japan -
Malaysia - Malta - Morocco - Philippines - Singapore - Spain - Sweden - Switzerland - United Kingdom - United States of America

www.st.com

