

**Qualification Results Summary of Revision to Thickness of Polyimide and  
Redistribution Layers for ADN8833 and ADN8834 in WLCSP**

QUALIFICATION PLAN			
TEST	SPECIFICATION	SAMPLE SIZE (LOT*SAMPLE)	RESULTS
Temperature Cycle (TC) -40C to +125C (1 cycle/hour) 500 cycles	JEDEC <i>JESD22-A104</i>	<b>3*77</b>	<b>Pass</b>
Unbiased HAST (UHAST) 130C / 85% RH 96 hours	JEDEC <i>JESD22-A118</i>	<b>3*25</b>	<b>Pass</b>
Electrostatic Discharge <i>Field-Induced Charged Device Model</i>	JEDEC <i>JS-002</i>	<b>1*18 3/voltage</b>	<b>Pass</b>